

Submitted to *Scripta Materialia*, July 2017. Revised September 2017.

Fabricating geometrically-complex B₄C ceramic components by robocasting and pressureless spark plasma sintering

Siamak Eqtesadi ^a, Azadeh Motealleh ^a, Fidel H. Perera ^b, Pedro Miranda ^b, Antonia Pajares ^b, Rune Wendelbo ^a, Fernando Guiberteau ^b, and Angel L. Ortiz ^{b,*}

^a Abalonyx AS, Oslo, Norway

^b Department of Mechanical, Energy, and Materials Engineering,
University of Extremadura, 06006 Badajoz, Spain

Abstract

Robocasting and pressureless spark plasma sintering are combined for the first time to fabricate geometrically-complex B₄C components. It is shown that robocasting allows B₄C green pieces to be printed with near-net shape from inks with suitable rheological properties, and that subsequent pressureless spark plasma sintering permits an ultrafast, energy-efficient, solid-state densification that yields B₄C parts with adequate mechanical properties. Furthermore, the usefulness of cold-isostatic pressing to improve the densification of the pieces is evaluated, and the benefits of robocasting over conventional dry powder compaction are identified. Finally, the scalability for the production of large B₄C pieces is discussed.

Keywords: B₄C; robocasting; pressureless spark plasma sintering; complex-shaped parts.

* Corresponding author:

Angel L. Ortiz

Phone: +34 924289600 Ext: 86726

Fax: +34 924289601

E-mail: alortiz@unex.es

1
2
3
4 Fabricating geometrically-complex ceramic articles with near-net shape is a long-sought
5
6 objective of the ceramic industry with a view to reducing, and ideally to eliminating, the
7
8 production costs associated with the post-sintering machining and finishing operations required
9
10 to extract complex shapes from pieces with simple geometries. The motivation soars for ultra-
11
12 hard ceramics because these operations can become prohibitively expensive and time-
13
14 consuming, even inviable in some cases. B_4C , also known as black diamond, is one of these
15
16 super-hard and ultralight engineering ceramics demanded at the industrial scale in parts with
17
18 complex geometries. For example, one B_4C application receiving great attention today is that of
19
20 personnel and vehicle armour components [1-4]. The former must have ergonomic designs to
21
22 protect body zones with different curvatures without penalizing mobility, and the latter custom
23
24 designs to offer maximal coverage of the chassis or fuselage without jeopardizing
25
26 maneuverability. Another major application of B_4C is in tribocomponents [1,2,5] such as nozzles
27
28 for blasting and water-jet cutting, cutting tools and dies, and other wear-resistant parts.
29
30

31
32 The near-net shape fabrication of a geometrically-complex ceramic article entails the
33
34 shaping of the corresponding green compact (normally by any wet or plastic forming method),
35
36 followed by its pressureless sintering. Unfortunately however, B_4C is hardly densifiable in the
37
38 pure state by conventional pressureless solid-state sintering [2]. Thus, hot-pressing is the
39
40 reference sintering technique for the consolidation of pure B_4C powders into dense pieces [2].
41
42 The undesirable consequence is then that the external uniaxial pressure and the confinement in
43
44 the die limit the production to simple geometries. Spark plasma sintering with pressure has the
45
46 same limitations, and hot-isostatic pressing is intrinsically problematic (glass encapsulation
47
48 problems) and therefore is used rather as a post-sintering complement [2]. Thus, there is a real
49
50
51
52
53
54
55
56
57
58
59
60
61
62
63
64
65

1
2
3
4 need to develop routes enabling the production of near-net shaped B₄C parts by the combination
5
6 of innovative forming and sintering techniques.
7

8
9 In this context, additive manufacturing techniques have opened new doors for preparing
10 ceramic green articles with complex shapes that are hardly or not-at-all manufacturable by
11 traditional ceramic processes. Robocasting (RC) is a unique additive manufacturing method
12 particularly well-suited to 3D-printing ceramic pieces. Green parts are built by extruding highly-
13 concentrated aqueous suspensions (inks) of the desired ceramic powders through a fine nozzle. A
14 robotic system moves the nozzle following a computer-aided design (CAD) model in order to
15 build the part layer by layer [6,7]. Meanwhile, electric current activated or assisted sintering
16 (ECAS) techniques have revolutionized the science of ceramic processing in general, especially
17 for these hard-to-sinter ceramics. Pressureless spark plasma sintering (PSPS) is one of these
18 novel ECAS techniques, consisting of the repeated application of high energy, low voltage,
19 pulsed direct electrical current [8,9], without the help of external pressure. This combination of
20 features enables the ultra-fast and energy-efficient densification of geometrically-complex
21 ceramic green parts.
22
23
24
25
26
27
28
29
30
31
32
33
34
35
36
37
38
39

40 Given the above, it seemed that it could be worth exploring the combination of RC with
41 PSPS as a solution to the problem of fabricating geometrically-complex B₄C components with
42 near-net shape. This study was aimed in this direction, to address two of the eight challenges [10]
43 with societal import recently identified by the ceramic community: (i) ceramic processing
44 through programmable design and assembly (*i.e.*, additive manufacturing, and RC in particular),
45 and (ii) ceramics for extreme environments (including specifically tribological, super-abrasive,
46 and armour materials).
47
48
49
50
51
52
53
54
55
56
57
58
59
60
61
62
63
64
65

1
2
3
4 With this idea in mind, we prepared an ink with 40 vol.% B₄C loading and minimal
5 organic content as follows. First, 1 wt.% (relative to B₄C content) of a synthetic polyelectrolyte
6 dispersant (Produkt KV5088, Zschimmer-Schwarz) was dissolved in deionized water at room
7 temperature and natural pH, and the solution was agitated (ARE-250, Thinky) for 10 min at 700
8 rpm. Second, the B₄C powder (Grade HD 20, H.C. Starck; $d_{10} \sim 0.1\text{--}0.36 \mu\text{m}$, $d_{50} \sim 0.3\text{--}0.6 \mu\text{m}$,
9 and $d_{90} \sim 0.9\text{--}1.5 \mu\text{m}$) was added in batches to this aqueous solution, each time agitating the
10 resulting suspension for 10 min at 800 rpm. Third, 7 mg/mL (in the final suspension) of
11 methylcellulose (Methocel F4M, $M_w = 3500 \text{ g/mol}$, 5 wt.%; Dow Chemical Company) was
12 introduced to viscosify the suspension, which was agitated for 10 min at 1000 rpm. Fourth, 4
13 vol.% (relative to liquid content) of polyethylenimine (PEI) flocculant (10% w/v in water,
14 Sigma-Aldrich) was added to gellify the suspension. And fifth, the resulting colloidal ink was
15 homogenized by agitation for 2 min at 1200 rpm followed by 7 min at 700 rpm.
16
17
18
19
20
21
22
23
24
25
26
27
28
29
30
31
32

33
34 Fig. 1 shows representative rheological properties of the B₄C ink developed, measured
35 using a rheometer (Discovery HR-2, TA Instruments Ltd.) configured in the parallel plate
36 geometry (40 mm, and gap of 800 μm), demonstrating its suitability for RC. Specifically, it is
37 seen in Fig. 1A that the ink has the shear-thinning flow behavior desirable for its extrusion as a
38 smooth filament without die swell. Moreover, it is seen in Fig. 1B that the ink also exhibits a
39 linear viscoelastic response at low stress with high values of stiffness ($\sim 2.5 \text{ MPa}$) and yield
40 strength ($\sim 50\text{--}60 \text{ Pa}$, corresponding to the onset of the sudden fall), as required for the extruded
41 filament to retain its form and support the weight of the layers above. B₄C inks were formulated
42 before using only PEI as both dispersant and binder and evaluated in terms of their rheological
43 behaviour and printability [11]. Compared to that work, the ink prepared here exhibits a storage
44
45
46
47
48
49
50
51
52
53
54
55
56
57
58
59
60
61
62
63
64
65

1
2
3
4 modulus two orders of magnitude higher, which in principle makes it more suitable for
5
6 producing parts with overhanging features or internal holes/gaps.
7
8

9 Fig. 2 shows optical images confirming the feasibility of obtaining geometrically-
10 complex B₄C green articles by RC from this ink. We have printed different bulk and porous parts
11 covering some typical B₄C applications (Figs. 2A-B). They include square and hexagonal plates
12 to build multi-segmented armour panels, gears of different sizes and morphologies for
13 tribological applications, conical nozzles with various dimensions and tip sizes for blasting and
14 water-jet cutting, and square and cylindrical porous elements for application as filters or catalytic
15 supports. In all cases, 3D printing (A3200, 3D inks) was done under ambient deposition
16 conditions using a conical nozzle (410 μm tip diameter, d) and a constant printing speed of 20
17 mm/s (corresponding to a flow rate of $\sim 2.64 \text{ mm}^3/\text{s}$). Most pieces were printed using a parallel
18 raster pattern with 342 μm ($d/1.2$) rod spacing, 356 μm ($d/1.15$) layer height, and 205 μm ($d/2$)
19 in-plane shifting between adjacent layers, which yields a hexagonal stacking of filaments (close
20 packed design; Fig. 2C) with optimal overlap, minimal excess ink overflow and without periodic,
21 inter-rod defects [12]. Conical pieces were printed using a circular raster pattern comprising 3
22 concentric rings with the same rod spacing and layer height as before, but variable in-plane layer
23 shifting depending on the desired cone angle. Porous B₄C elements were printed adopting a
24 tetragonal mesh with 820 μm ($2d$) rod spacing and 328 μm ($d/1.2$) layer height. As-printed parts
25 were then dried for 48 h, yielding robust bulk green parts which, relative to the CAD model,
26 shrank laterally and vertically by $\sim 3 \pm 1\%$ and $\sim 5 \pm 1\%$ respectively, and by $\sim 4 \pm 1\%$ and $\sim 7 \pm 1\%$ if
27 post-isopressed ($\sim 1\text{--}2\%$ additional isotropic shrinkage with respect to the dried green part).
28 These slight differences between in-plane and out-of-plane dimensions is not attributed to any
29 anisotropy during drying but rather to a minimal shape distortion occurring during printing due
30
31
32
33
34
35
36
37
38
39
40
41
42
43
44
45
46
47
48
49
50
51
52
53
54
55
56
57
58
59
60
61
62
63
64
65

1
2
3
4 to both gravity and lateral overflow of excess ink. Nevertheless, if required to meet tolerances,
5
6 this small shape deviation could be easily corrected by conveniently adjusting the initial CAD
7
8 model dimensions.
9

10
11 As shown in Fig. 2D, the relative green density of as-dried robocast (RC) B₄C bulk parts,
12
13 measured on square plates from their mass and external dimensions, is ~53±2%, increasing up to
14
15 ~58±2% with the subsequent cold-isostatic pressing (RC+CIP) at 200 MPa (which preserved
16
17 shape). The reference cylindrical compacts prepared from the B₄C powders by cold-uniaxial
18
19 pressing (CP) at 50 MPa and by cold-uniaxial pressing at 50 MPa plus cold-isostatic pressing
20
21 (CP+CIP) at 200 MPa have relative densities of ~45±1% and ~51±2% (~4±1% isotropic
22
23 shrinkage with respect to the uniaxially-pressed compact), respectively. Therefore, the B₄C parts
24
25 shaped by RC have denser green microstructures than the articles shaped by conventional dry
26
27 isostatic pressing (CP+CIP). This is attributable to the wet route favouring the sliding and
28
29 rearrangement of the B₄C faceted particles to a greater packing, but this observation does not
30
31 imply generality.
32
33
34
35
36
37

38
39 Having demonstrated the versatility of RC in producing highly dense geometrically-
40
41 complex B₄C green parts, we next studied their pressureless spark plasma sinterability. The study
42
43 was conducted on both as-robocast and post-isopressed green samples with square plate
44
45 morphology to facilitate the subsequent measurements of density and shrinkage, with the
46
47 cylindrical counterparts prepared by conventional dry pressing serving as reference baseline.
48
49 PSPS was done (HP-D-10, FCT Systeme GmbH) in a dynamic vacuum (~3 Pa) at 1900, 2000, or
50
51 2100 °C for 5 min, using a heating ramp of 100 °C/min. A special graphite die assembly with
52
53 circular geometry was used to avoid load application on the B₄C pieces, which rested on the
54
55 lower punch. Included in Fig. 2D are also the relative densities of all sintered pieces. As
56
57
58
59
60
61
62
63
64
65

1
2
3
4 expected, the relative density of the robocast pieces (RC) increases from $\sim 74\pm 3$ to $90\pm 3\%$ with
5
6 increasing sintering temperature from 1900 to 2100 °C. Relative to CAD model, these pieces
7
8 shrank laterally and vertically from $\sim 9\pm 1\%$ and $\sim 12\pm 1\%$ at 1900 °C up to $\sim 17\pm 1\%$ and $\sim 21\pm 2\%$
9
10 at 2100 °C, respectively. Therefore, within experimental errors, they seem to have shrunk
11
12 isotropically during sintering (additional shrinkages of $\sim 6\text{--}7\%$ at 1900 °C and $\sim 14\text{--}16\%$ at 2100
13
14 °C). If isostatically pressed (RC+CIP), these pieces reach near-full densification ($\sim 95\pm 3\%$) at
15
16 2100 °C, with total lateral and vertical shrinkages relative to the CAD model of $\sim 20\pm 2\%$ and
17
18 $\sim 24\pm 1\%$, respectively. Therefore, the isopressed pieces seem to have shrunk also isotropically
19
20 during sintering ($\sim 16\text{--}17\%$ additional shrinkage), thus preserving the shape of the corresponding
21
22 green piece. This temperature is lower and the soaking time much shorter than typically required
23
24 (several hours at ~ 2300 °C) for pure B₄C powders to reach densifications greater than 90% by
25
26 conventional pressureless solid-state sintering [2]. This result puts the advantages of PSPS into
27
28 perspective –without any demerit to the major densification achieved in the green state by RC,
29
30 especially when combined with CIP. Essentially, the ultrafast heating in PSPS allows high
31
32 enough temperatures to be rapidly reached having eliminated the oxidic impurities, conditions at
33
34 which densification is favored over coarsening. Interestingly, under identical sintering
35
36 conditions, the pieces shaped by RC densified more (by $\sim 6\%$) than their reference counterparts
37
38 shaped by conventional dry pressing. This is attributable to the former having greater green-body
39
40 densification –indeed, the same $\sim 7\text{--}8\%$ difference in density existed already in the green state.
41
42 This same reason explains why robocast (RC) pieces reached essentially the same densification
43
44 at 2000 °C as the uniaxial-pressed (CP) ones at 2100 °C. All these results confirm that shaping
45
46 by RC is recommendable over the conventional dry-pressing route, at least for the particular B₄C
47
48 powder used.
49
50
51
52
53
54
55
56
57
58
59
60
61
62
63
64
65

1
2
3
4 The observations by scanning-electron microscopy (SEM; Quanta 3D FEG, FEI) of
5 fracture surfaces created in B₄C sintered pieces, such as those shown in Fig. 3, corroborate the
6
7 deductions made from the density measurements. It is seen that the pieces shaped by RC are (i)
8
9 very porous at 1900 °C, reaching only the early stage of the intermediate sintering regime (Fig.
10
11 3A), (ii) partially dense at 2000 °C, reaching the middle stage of the intermediate sintering
12
13 regime (Fig. 3B), and (iii) very dense at 2100 °C, reaching the early stage of the final sintering
14
15 regime (Fig. 3C). If isostatically pressed, the piece shaped by RC becomes near fully-dense at
16
17 2100 °C, reaching the later stage of the final sintering regime (Fig. 3D). Comparatively, at 2100
18
19 °C, the pieces shaped by dry uniaxial pressing (Fig. 3E) and by dry uniaxial+isostatic pressing
20
21 (Fig. 3F) are only at the middle stage of the intermediate sintering regime and the later stage of
22
23 the intermediate sintering regime, respectively.
24
25
26
27
28
29
30

31 Fig. 4 shows the hardness and compressive strength of the sintered B₄C ceramics. The
32
33 former was evaluated by Vickers indentation tests (MV-1, Matsuzawa) at 49 N load, and the
34
35 latter was measured (on 3.2×3.2×5.5 mm³ parallelepipeds) by uniaxial compression tests
36
37 (Hoytom 200kN, Hoytom S.L.) at a constant crosshead speed of 0.6 mm/min up to failure. In
38
39 both cases the samples were placed with their printing plane (robocast ceramics) or their
40
41 uniaxial-compaction plane (dry-pressed ceramics) perpendicular to the load axis. It is seen that
42
43 both magnitudes increase (i) with increasing sintering temperature, and (ii) with the use of
44
45 isostatic pressing, and that they are greater for the ceramics shaped by RC. Therefore, it is clear
46
47 that both hardness and compressive strength correlate directly with the densification degree,
48
49 increasing as the residual porosity decreases. The hardest and strongest of the present B₄C
50
51 ceramics (RC+CIP) has, despite its ~5% residual porosity, a hardness of ~27 GPa and a
52
53 compressive strength of ~1800 MPa. This is an excellent combination of mechanical properties
54
55
56
57
58
59
60
61
62
63
64
65

1
2
3
4 because B₄C ceramics fabricated by conventional pressureless sintering have lower hardness
5 values (18–24 GPa) [2], and the compressive strength is within the range (1400–3400 MPa)
6 typically measured for B₄C ceramics fabricated by hot-pressing [2]. Remarkably, the B₄C
7 ceramic shaped by RC only (without CIP) and then PSPS-ed at 2100 °C also exhibits, despite its
8 ~10% residual porosity, hardness and compressive strength values in these intervals (~20.5 GPa
9 and ~1450 MPa, respectively), which is not the case for any of the two B₄C ceramics shaped by
10 conventional dry-pressing techniques. Despite these outstanding results, there is still plenty of
11 room for optimizing the proposed fabrication route –RC followed by PSPS, with or without an
12 intervening CIP step– by tailoring the PSPS cycle. Future work in this direction (beyond the
13 scope of this first proof-of-concept study) is expected to further reduce the residual porosity in
14 the B₄C ceramics, enabling them to reach super-high hardness and compressive strength values.
15 Indeed, the hardness of B₄C ceramics seems to increase exponentially with a rate constant of ~7
16 as the residual porosity decreases [13], so that hardness values as high as 35 GPa are anticipated
17 for such dense B₄C ceramics.
18
19
20
21
22
23
24
25
26
27
28
29
30
31
32
33
34
35
36
37

38 In conclusion, the present work demonstrates the feasibility of successfully fabricating
39 geometrically-complex B₄C ceramic parts with near-net shape and appropriate mechanical
40 properties by combining RC with PSPS. This combination might have extensive practical
41 implications, and may turn many what are now industrial aspirations for B₄C into reality. In
42 principle, the proposed processing route is scalable for the commercial production of large pieces
43 given that there are already large RC devices and SPS units available on the market. PSPS is
44 very energy efficient, which becomes especially important in the fabrication of large parts made
45 from highly refractory ceramics. And for the sintering of large pieces, there exist SPS units
46 equipped with inductive heating systems that prevent radial temperature gradients and with
47
48
49
50
51
52
53
54
55
56
57
58
59
60
61
62
63
64
65

1
2
3
4 robotized systems that handle both placing the green parts in the chamber and extracting the
5
6 sintered articles. The most limiting factor would be the printing times of large components in
7
8 RC, but this can be conveniently adjusted without penalizing the dimensional accuracy by
9
10 judicious control of the tip size and extrusion speed. Besides, the versatility of RC will directly
11
12 enable curved or internally-complex pieces to be manufactured—if necessary, with the aid of
13
14 fugitive inks that are to be eliminated before or during sintering [14]— and pieces with smoothly
15
16 graded compositions can easily be built by using various ink dispersers and a mixing head.
17
18
19
20
21
22

23
24 This work was financially supported by the Ministerio de Economía y Competitividad
25
26 (Government of Spain) under grant nº MAT2016-76638-R), and by the Junta de Extremadura
27
28 under grants nº IB16094 and GR15078, all co-financed with FEDER Funds.
29
30
31
32
33
34
35
36
37
38
39
40
41
42
43
44
45
46
47
48
49
50
51
52
53
54
55
56
57
58
59
60
61
62
63
64
65

References

1. F. Thevenot, *J. Eur. Ceram. Soc.* 6 (1990) 205–225.
2. A. Suri, C. Subramanian, J. Sonber, T. Murthy, *Int. Mater. Rev.* 55 (2010) 4–39.
3. S. Leo, C. Tallon, G.V. Franks, *J. Am. Ceram. Soc.* 97 (2014) 3013–3033.
4. V. Domnich, S. Reynaud, R.A. Haber, M. Chhowalla, *J. Am. Ceram. Soc.* 94 (2011) 3605–3628.
5. B.M. Moshtaghioun, D. Gomez-Garcia, A. Dominguez-Rodriguez, R.I. Todd, *J. Eur. Ceram. Soc.* 36 (2016) 3925–3928.
6. J.A. Lewis, J.E. Smay, J. Stuecker, J. Cesarano, *J. Am. Ceram. Soc.* 89 (2006) 3599–3609.
7. P. Miranda, E. Saiz, K. Gryn, A.P. Tomsia, *Acta Biomater.* 2 (2006) 457–466.
8. R. Orru, R. Licheri, A.M. Locci, A. Cincotti, G. Cao, *Mat. Sci. Eng. R* 63 (2009) 127–287.
9. Z.A. Munir, D.V. Quach, M. Ohyanagi, *J. Am. Ceram. Soc.* 94 (2011) 1–19.
10. K.T. Faber, T. Asefa, M. Backhaus-Ricoult, R.K. Brow, J. Chan, S. Dillon, W.G. Fahrenholtz, M.W. Finnis, J.E. Garay, E. Garcia, Y. Gogotsi, S.M. Haile, J.W. Halloran, J. Hu, L. Huang, S. Jacobsen, E. Lara-Curzio, J. LeBeau, W.E. Lee, C.G. Levi, I. Levin, J.A. Lewis, D.M. Lipkin, K. Lu, J. Luo, J.P. Maria, L.W. Martin, S. Martin, G.L. Messing, A. Navrotsky, N.P. Padture, C.A. Randall, G.S. Rohrer, A. Rozenflanz, T. Schaedler, D. Schlom, A. Sehirlioglu, A. Stevensen, T. Tani, V. Tikare, S. Trolier-McKinstry, H. Wang, and B. Yildiz, *J. Am. Ceram. Soc.* 100 [5] (2017) 1777–1803.
11. W.J. Costakis Jr., L.M. Rueschhoff, A.I. Diaz-Cano, J.P. Youngblood, R.W. Trice, *J. Eur. Ceram. Soc.* 36 (2016) 3249–3256.
12. E. Feilden, E. García-Tuñón, F. Giuliani, E. Saiz, L. Vandeperre, *J. Eur. Ceram. Soc.* 36 (2016) 2525–2533.

1
2
3
4
5
6
7
8
9
10
11
12
13
14
15
16
17
18
19
20
21
22
23
24
25
26
27
28
29
30
31
32
33
34
35
36
37
38
39
40
41
42
43
44
45
46
47
48
49
50
51
52
53
54
55
56
57
58
59
60
61
62
63
64
65

13. B.M. Moshtaghioun, D. Gomez-Garcia, A. Dominguez-Rodriguez, R.I. Todd, J. Eur. Ceram. Soc. 36 (2016) 1829–1834.

14. F.J. Martínez-Vázquez, A. Pajares, P. Miranda, J. Eur. Ceram. Soc (2017), under review.

1
2
3
4 **Figure Captions**
5
6
7

8 **Figure 1.** Rheological characterization of the B₄C ink used in the shaping by RC showing
9 specifically the logarithmic plots of (A) viscosity vs shear rate and (B) storage modulus vs shear
10 stress. Points are the experimental data, and the solid lines are just to guide the eye.
11
12
13
14

15
16
17 **Figure 2.** (A) Optical image captured *in situ* during the 3D printing of a geometrically-complex
18 circular gear. (B) Optical images of several B₄C green parts shaped by RC, and then dried. (C)
19 View of a simple computer-aided design model showing the parallel raster pattern used. (D)
20 Relative density (average of at least 3 measurements) of both the B₄C green and the sintered
21 parts for the different shaping procedures and sintering temperatures used.
22
23
24
25
26
27
28
29

30
31 **Figure 3.** SEM micrographs of fracture surfaces of the B₄C sintered ceramics prepared under the
32 pairs of shaping procedure–PSPS temperature indicated.
33
34
35
36
37

38
39 **Figure 4.** Vickers hardness and compressive strength of the B₄C sintered parts for the different
40 shaping procedures and sintering temperatures used.
41
42
43
44
45
46
47
48
49
50
51
52
53
54
55
56
57
58
59
60
61
62
63
64
65









